

Mudfords

SUPPLIERS TO INDUSTRY, TRANSPORT AND CONSTRUCTION

Mudfords Ltd, Registered in England No. 2632883 Registered Office: 400 Petre Street, Sheffield, South Yorkshire S4 8LU

E-mail: sales@mudfords.co.uk Website: www.mudfords.co.uk

TECHNICAL SPECIFICATIONS

Insulated Tarpaulin - Premium

PVC - UPPER

BASE FABRIC	POLYESTER 1100 DTEX (1000) DENIER
CONSTRUCTION	PLAIN WEAVE 7 X 7/CM
WEIGHT	610GSM
TENSILE STRENGTH	2000/2000 N/5CM
TEAR STRENGTH	250/250 N
COATING ADHESION	100/100 N/5CM
TEMPERATURE	- 30 + 70°

NON WOVEN NEEDLEPUNCH FELT - INNER

No known occupational exposure limit.

No known synergistic reactions with other materials at normal temperatures and conditions.

Store in dry conditions away from toxic vapours.

In the event of fire the application of water is quite safe, but in confined space toxic gases will very quickly be generated. Large fires should be controlled by the fire brigade.

No relevant tests applicable eg flammability or toxicity.

14oz BEFORE PROOFING COTTON DUCK - BASE

Rot Resistance

0=	Nil	
1=	BS2087:1992:4.5.3 (a - light process)	1.0% PCPL
2=	BS2087:1992:4.5.3 (b - normal process)	1.7% PCP:
3=	BS2087:1992:4.3.3 (b - special process)	0.5 - 1.0% Copper As Cupramonium
4=	BS2087:1992:4.3.3 (a - normal process)	1.0% - 1.5% Copper As Cupramonium
5=	BS2087:1992:4.2.3	0.5 - 1.2 % Copper As Copper Napthanate

Water Resistance

0=	Nil	
1=	BS 3408:1992, 3.3.7 (method B2	- (Appendix B, B2, B3.2 - Before Soaking Test
2=	BS EN 20811: 1992	- (Hydrostatic Head Test)
3=	BS 4F 100:1982	- Bandesmann Type Shower Test

400 Petre Street
Sheffield
S4 8LU
Tel: 0114 243 3033
Fax: 0114 244 4536



Mudfords Ltd Sheffield
Cert No 9407



Alverthorpe Road
Wakefield
WF2 9NT
Tel: 01924 364 771
Fax: 01924 291 725